

### Product Data Sheet

# E 8/2 V2H/V2H MT/MT red FDA

#### Applications

Food industry

#### Order information

Article number	907170
Suitable for corrugated side walls	No
Standard delivery width	2100 mm / 82.68 in
Longitudinal seam possible	Yes

#### Construction

Top face material	Polyvinyl chloride, hard
Surface pattern	Matte
Coating thickness	0.2 mm / 0.008 in
Color	Red
Driving face material	Polyvinyl chloride, hard
Surface pattern	Matte
Coating thickness	0.2 mm / 0.008 in
Color	Red
Tension member material	Laterally stiff fabric of polyester warp and weft
Number of fabric plies	2
Driving face weave	Both sides coated

### E 8/2 V2H/V2H MT/MT red FDA

#### Technical data

<b>Total thickness</b>	2.6 mm ± 0.15 0.102 in ± 0.006
<b>Weight</b>	3.2 kg/m <sup>2</sup> ± 0.2 0.655 lbs/ft <sup>2</sup> ± 0.041
<b>k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005</b>	5.5 N/mm / 31.41 lbf/in
<b>Recommended Elongation at fitting min.</b>	0.3 %
<b>Recommended Elongation at fitting max.</b>	1 %
<b>Friction coefficient of driving face against steel panel according ISO 21182</b>	0.2
<b>Friction coefficient of top face against steel panel according ISO 21182</b>	0.25
<b>Permissible operating temperature</b>	-10/70 °C, for a short time 90 °C 14/158 °F, for a short time 194 °F
<b>Hardness of top face coating as per DIN 53505 (Shore A)</b>	92

#### Properties

<b>Lateral stiffness</b>	Laterally stiff
<b>Troughable</b>	No
<b>Suitable for accumulation</b>	No
<b>Inclined conveying</b>	No
<b>Suitable for knife edges</b>	No
<b>Suitable for curves</b>	No
<b>Flame-retardant</b>	No
<b>Noise development</b>	Normal
<b>Belt support</b>	Slider bed (support rollers possible)

### E 8/2 V2H/V2H MT/MT red FDA

#### Food properties

<b>FDA 21CFR</b>	Suitable for the transport of unpacked Food in compliance with FDA regulation 21CFR
<b>Halal</b>	Certificated Halal product. Meets trade description order 2011 and CODEX Alimentarius 1997 guidelines under supervision of Islamic Food Research Centre Hong Kong & Asia Region

#### Electrostatic properties

<b>Antistatic</b>	Belt material with an electrically conductive antistatic agent. Volume resistance (RDi) in longitudinal direction parallel to plane of belt <math>< 3 \times 10^8 \Omega</math>. Measurement according DIN EN ISO 21178.
-------------------	--

#### Fabrication

<b>Belt edge sealing</b>	Smartseal
<b>Suitable for corrugated side walls</b>	No
<b>Profiles on top face</b>	On request
<b>Profiles on underside</b>	On request
<b>Mechanical fasteners</b>	On request

#### Minimum drum diameter

<b>Z-splice, counter-bending</b>	100 mm / 3.9 in
----------------------------------	-----------------

#### Remarks

<b>Chemical resistance</b>	V-FDA
----------------------------	-------

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations. See our brochure "Technical Information 1" no. 317 which shows the types of belts that can be supplied and the manufacturing tolerances. Customised types require written confirmation.

Date of last change: 4/15/2026 7:08:24 AM

