

Product Data Sheet

PVC150 RTxB-NA black FR



Art. No.: 908018

M 1:2

Applications

Airport logistics

General material handling Inclined conveying of unit goods / containers

Logistics Braking conveyor

Order information

Article number 908018

Suitable for corrugated side walls No

Belt style PVC = Interwoven PVC

Standard delivery width 1829 mm / 72.01 in

Longitudinal seam possible Yes

PVC150 RTxB-NA black FR

Construction

Top face material	Polyvinyl chloride, low durometer
Surface pattern	Rough-top, fabric embossing
Coating thickness	5.08 mm / 0.2 in
Color	Black
Driving face material	Polyester fabric, brushed
Surface pattern	Fabric, coarse
Color	Black
Tension member material	2-ply interwoven fabric of polyester spun warp and weft
Number of fabric plies	1

Technical data

Total thickness	7.37 mm ± 0.25 0.29 in ± 0.01
Weight	5.86 kg/m ² ± 0.59 1.2 lbs/ft ² ± 0.12
k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005	8 N/mm / 45.68 lbf/in
Recommended Elongation at fitting min.	0.5 %
Recommended Elongation at fitting max.	1.5 %
Rated working tension	26 N/mm / 150 lbf/in at 2 % Elongation
Friction coefficient of driving face against steel panel according ISO 21182	0.35
Permissible operating temperature	-18/82 °C 0/180 °F
Hardness of top face coating as per DIN 53505 (Shore A)	55

PVC150 RTxB-NA black FR

Properties

Lateral stiffness	Laterally flexible
Troughable	Yes
Suitable for accumulation	No
Inclined conveying	Yes
Suitable for knife edges	No
Suitable for curves	No
Flame-retardant	FR (ASTM D-378)
Noise development	Normal
Particular surface properties	▸ High Grip
Belt support	Slider bed (support rollers possible)
UV resistance	Normal

Electrostatic properties

Not antistatic	Belt material with electrically insulating properties
-----------------------	---

Fabrication

Suitable for corrugated side walls	No
Profiles on top face	No
Profiles on underside	Yes
Mechanical fasteners	On request

Minimum drum diameter

Z-splice, counter-bending	89 mm / 3.5 in
----------------------------------	----------------

Remarks

Chemical resistance	Good
----------------------------	------

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 3/12/2024 10:38:30 AM