


## Product Data Sheet

# PVC350 O/M CxB black FR



Art. No.: 908312

M 1:2

### Applications

#### Agriculture

**General material handling** Waste conveyor, recycling conveyor

**Steel** Metal cutting line/shearing line

### Order information

**Article number** 908312

**Suitable for corrugated side walls** No

**Belt style** PVC = Interwoven PVC

**Standard delivery width** 1829 mm / 72.01 in

**Longitudinal seam possible** Yes

### PVC350 O/M CxB black FR

#### Construction

<b>Top face material</b>	Polyvinyl chloride, hard
<b>Surface pattern</b>	Smooth
<b>Coating thickness</b>	1.02 mm / 0.04 in
<b>Color</b>	Black
<b>Driving face material</b>	Polyester fabric, brushed
<b>Surface pattern</b>	Fabric, coarse
<b>Color</b>	Black
<b>Tension member material</b>	2-ply interwoven fabric of polyester spun and filament warp and weft
<b>Number of fabric plies</b>	1

#### Technical data

<b>Total thickness</b>	6.35 mm ± 0.32 0.25 in ± 0.013
<b>Weight</b>	8.3 kg/m <sup>2</sup> ± 0.41 1.7 lbs/ft <sup>2</sup> ± 0.085
<b>k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005</b>	16.64 N/mm / 95 lbf/in
<b>Recommended Elongation at fitting min.</b>	0.5 %
<b>Recommended Elongation at fitting max.</b>	1.5 %
<b>Rated working tension</b>	61 N/mm / 350 lbf/in at 2 % Elongation
<b>Friction coefficient of driving face against steel panel according ISO 21182</b>	0.3
<b>Friction coefficient of top face against steel panel according ISO 21182</b>	0.85
<b>Permissible operating temperature</b>	-18/82 °C 0/180 °F
<b>Hardness of top face coating as per DIN 53505 (Shore A)</b>	80

### PVC350 O/M CxB black FR

#### Properties

<b>Lateral stiffness</b>	Laterally stiff
<b>Troughable</b>	Limited
<b>Suitable for accumulation</b>	No
<b>Inclined conveying</b>	No
<b>Suitable for knife edges</b>	No
<b>Suitable for curves</b>	No
<b>Flame-retardant</b>	FR (ASTM D-378 & MSHA 2G)
<b>Noise development</b>	Normal
<b>Particular surface properties</b>	► Good grip
<b>Belt support</b>	Slider bed (support rollers possible)
<b>UV resistance</b>	Normal

#### Electrostatic properties

OSHA 29 CFR

#### Fabrication

<b>Suitable for corrugated side walls</b>	No
<b>Profiles on top face</b>	Yes
<b>Profiles on underside</b>	Yes
<b>Mechanical fasteners</b>	Alligator®RS187

#### Minimum drum diameter

<b>Mechanical Alligator® fastener, bending</b>	152 mm / 6 in
<b>Z-splice, bending</b>	152 mm / 6 in

#### Remarks

► High mechanical fastener retention.

<b>Chemical resistance</b>	V
----------------------------	---

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN

## PVC350 O/M CxB black FR

50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 8/29/2024 10:49:52 AM