

Product Data Sheet

PVC120 OFR-80A CTxF-NA white FDA



Art. No.: 908313

M 1:2

Applications

Agriculture	Harvesting machines; Processing of fruits and vegetables (also oily and fatty)
Candy industry	
Fish industry & meat industry	Meat processing
Food industry	Processing of food (also oily and fatty)
General material handling	Horizontal conveying and inclined conveying of small components / bulky goods; Troughed conveyor belt

Order information

Article number	908313
Suitable for corrugated side walls	No
Belt style	PVC = Interwoven PVC
Standard delivery width	1829 mm / 72.01 in
Longitudinal seam possible	Yes

PVC120 OFR-80A CTxF-NA white FDA

Construction

Top face material	Polyvinyl chloride, oil and fat resistant
Surface pattern	Crescent top
Coating thickness	5.08 mm / 0.2 in
Color	White
Driving face material	Polyvinyl chloride, oil and fat resistant
Surface pattern	Fabric
Coating thickness	0.1 mm / 0.004 in
Color	White
Tension member material	2-ply interwoven fabric of polyester spun warp and weft
Number of fabric plies	1

Technical data

Total thickness	5.59 mm \pm 0.25 0.22 in \pm 0.01
Weight	4.15 kg/m ² \pm 0.42 0.85 lbs/ft ² \pm 0.085
k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005	8.5 N/mm / 48.54 lbf/in
Recommended Elongation at fitting min.	0.5 %
Recommended Elongation at fitting max.	1.5 %
Rated working tension	21 N/mm / 120 lbf/in at 2 % Elongation
Friction coefficient of driving face against steel panel according ISO 21182	0.49
Permissible operating temperature	-18/82 °C 0/180 °F
Hardness of top face coating as per DIN 53505 (Shore A)	80

PVC120 OFR-80A CTxF-NA white FDA

Properties

Lateral stiffness	Laterally flexible
Troughable	Yes
Suitable for accumulation	No
Inclined conveying	Yes
Suitable for knife edges	No
Suitable for curves	Yes
Flame-retardant	No
Noise development	Normal
Particular surface properties	► High Grip
Belt support	Support rollers
UV resistance	Normal

Food properties

FDA 21CFR	Suitable for the transport of unpacked Food in compliance with FDA regulation 21CFR
-----------	---

Electrostatic properties

Not antistatic	Belt material with electrically insulating properties
----------------	---

Fabrication

Suitable for corrugated side walls	No
Profiles on top face	No
Profiles on underside	Yes
Mechanical fasteners	On request

Minimum drum diameter

Z-splice, counter-bending	76 mm / 3 in
---------------------------	--------------

PVC120 OFR-80A CTxF-NA white FDA

Remarks

Chemical resistance	Good
---------------------	------

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 3/12/2024 10:38:30 AM