

Product Data Sheet

PVC200 OFR CxF-NA white FDA



Art. No.: 908707

M 1:2

Applications

Agriculture	Processing of fruits and vegetables (also oily and fatty)
Food industry	Processing of food (also oily and fatty); Sorter belt
General material handling	Horizontal conveying (metering); Troughed conveyor belt

Order information

Article number	908707
Suitable for corrugated side walls	Yes
Belt style	PVC = Interwoven PVC
Standard delivery width	1829 mm / 72.01 in
Longitudinal seam possible	Yes

PVC200 OFR CxF-NA white FDA

Construction

Top face material	Polyvinyl chloride, oil and fat resistant
Surface pattern	Smooth
Coating thickness	1.02 mm / 0.04 in
Color	White
Driving face material	Polyvinyl chloride, oil and fat resistant
Surface pattern	Fabric
Coating thickness	0.1 mm / 0.004 in
Color	White
Tension member material	3-ply interwoven fabric of polyester spun warp and weft
Weave pattern	1

Technical data

Total thickness	5.08 mm \pm 0.25 0.2 in \pm 0.01
Weight	6.35 kg/m ² \pm 0.63 1.3 lbs/ft ² \pm 0.13
k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005	10.5 N/mm / 59.96 lbf/in
Recommended Elongation at fitting min.	0.5 %
Recommended Elongation at fitting max.	1.5 %
Rated working tension	35 N/mm / 200 lbf/in at 2 % Elongation
Friction coefficient of driving face against steel panel according ISO 21182	0.8
Friction coefficient of top face against steel panel according ISO 21182	0.9
Permissible operating temperature	-18/82 °C -0/180 °F
Hardness of top face coating as per DIN 53505 (Shore A)	80

PVC200 OFR CxF-NA white FDA

Properties

Lateral stiffness	Laterally flexible
Troughable	Yes
Suitable for accumulation	No
Inclined conveying	No
Suitable for knife edges	No
Suitable for curves	No
Flame-retardant	No
Noise development	Normal
Particular surface properties	► Good grip
Belt support	Support rollers
UV resistance	Good

Food properties

FDA 21CFR	Suitable for the transport of unpacked Food in compliance with FDA regulation 21CFR
-----------	---

Electrostatic properties

Not antistatic	Belt material with electrically insulating properties
----------------	---

Fabrication

Suitable for corrugated side walls	Yes
Profiles on top face	Yes
Profiles on underside	Yes
Mechanical fasteners	On request

Minimum drum diameter

Z-splice, counter-bending	102 mm / 4 in
---------------------------	---------------

PVC200 OFR CxF-NA white FDA

Remarks

Chemical resistance	Good
---------------------	------

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 3/12/2024 10:38:30 AM