

## Product Data Sheet

# PVC120 P CVT2xF-NA black



Art. No.: 908723

M 1:2

### Applications

<b>Agriculture</b>	Harvesting machines
<b>General material handling</b>	Horizontal conveying and inclined conveying of small components / bulky goods; Troughed conveyor belt

### Order information

<b>Article number</b>	908723
<b>Suitable for corrugated side walls</b>	No
<b>Belt style</b>	PVC = Interwoven PVC
<b>Standard delivery width</b>	1829 mm / 72.01 in
<b>Longitudinal seam possible</b>	Yes

### PVC120 P CVT2xF-NA black

#### Construction

<b>Top face material</b>	Polyvinyl chloride
<b>Surface pattern</b>	Chevron top, standard
<b>Coating thickness</b>	5.08 mm / 0.2 in
<b>Color</b>	Black
<b>Driving face material</b>	Polyvinyl chloride
<b>Surface pattern</b>	Fabric
<b>Coating thickness</b>	0.1 mm / 0.004 in
<b>Color</b>	Black
<b>Tension member material</b>	2-ply interwoven fabric of polyester spun warp and weft
<b>Weave pattern</b>	1

#### Technical data

<b>Total thickness</b>	6.1 mm $\pm$ 0.25 0.24 in $\pm$ 0.01
<b>Weight</b>	4.15 kg/m <sup>2</sup> $\pm$ 0.42 0.85 lbs/ft <sup>2</sup> $\pm$ 0.085
<b>k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005</b>	8.5 N/mm / 48.54 lbf/in
<b>Recommended Elongation at fitting min.</b>	0.5 %
<b>Recommended Elongation at fitting max.</b>	1.5 %
<b>Rated working tension</b>	21 N/mm / 120 lbf/in at 2 % Elongation
<b>Friction coefficient of driving face against steel panel according ISO 21182</b>	0.8
<b>Permissible operating temperature</b>	-18/82 °C -0/180 °F
<b>Hardness of top face coating as per DIN 53505 (Shore A)</b>	65

### PVC120 P CVT2xF-NA black

#### Properties

Lateral stiffness	Laterally flexible
Troughable	Yes
Suitable for accumulation	No
Inclined conveying	Yes
Suitable for knife edges	No
Suitable for curves	Yes
Flame-retardant	No
Noise development	Normal
Belt support	Support rollers
UV resistance	Normal

#### Electrostatic properties

Not antistatic	Belt material with electrically insulating properties
----------------	---

#### Fabrication

Suitable for corrugated side walls	No
Profiles on top face	No
Profiles on underside	Yes
Mechanical fasteners	On request

#### Minimum drum diameter

Z-splice, counter-bending	76 mm / 3 in
---------------------------	--------------

#### Remarks

Chemical resistance	Good
---------------------	------

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 3/12/2024 10:38:30 AM