

Product Data Sheet

PU150 HCxB-NA red



Art. No.: 908892

M 1:2

Applications

Metalworking & automotive industry	Punch press belt; Transport of metal parts; Wrapper belt for coil machinery in steel and aluminium processing
---	---

Order information

Article number	908892
Suitable for corrugated side walls	Yes
Belt style	PU = Polyurethane
Standard delivery width	1829 mm / 72.01 in
Longitudinal seam possible	Yes

PU150 HCxB-NA red

Construction

Top face material	Polyurethane, hard
Surface pattern	Smooth
Coating thickness	2.03 mm / 0.08 in
Color	Red
Driving face material	Polyester fabric, brushed
Surface pattern	Fabric, coarse
Color	Red
Tension member material	2-ply interwoven fabric of polyester spun warp and weft
Number of fabric plies	1
Remarks to tension member	Carcass impregnated with oil and fat resistant polyvinylchloride

Technical data

Total thickness	5.08 mm ± 0.25 0.2 in ± 0.01
Weight	5.86 kg/m ² ± 0.59 1.2 lbs/ft ² ± 0.12
k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005	11 N/mm / 62.81 lbf/in
Recommended Elongation at fitting min.	0.5 %
Recommended Elongation at fitting max.	1.5 %
Rated working tension	26 N/mm / 150 lbf/in at 2 % Elongation
Friction coefficient of driving face against steel panel according ISO 21182	0.35
Friction coefficient of top face against steel panel according ISO 21182	1
Permissible operating temperature	-29/82 °C -20/180 °F
Hardness of top face coating as per DIN 53505 (Shore A)	90

PU150 HCxB-NA red

Properties

Lateral stiffness	Laterally flexible
Troughable	No
Suitable for accumulation	No
Inclined conveying	No
Suitable for knife edges	No
Suitable for curves	No
Flame-retardant	No
Noise development	Normal
Particular surface properties	<ul style="list-style-type: none"> ▶ Good grip ▶ Coating/fabric high abrasion resistant ▶ High cut resistance ▶ Adhesive
Belt support	Slider bed (support rollers possible)
UV resistance	Normal

Electrostatic properties

Not antistatic	Belt material with electrically insulating properties
-----------------------	---

Fabrication

Suitable for corrugated side walls	Yes
Profiles on top face	Yes
Profiles on underside	Yes
Mechanical fasteners	On request

Minimum drum diameter

Z-splice, counter-bending	76 mm / 3 in
----------------------------------	--------------

Remarks

Chemical resistance	Very Good
----------------------------	-----------

The physical data in this data sheet is approximate, can alter depending on production environments and was

PU150 HCxB-NA red

established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 3/12/2024 10:38:30 AM