

### Product Data Sheet

# PF200 LT AR OFR CxF-NA blue FDA



Art. No.: 908922

M 1:2

### Applications

<b>Agriculture</b>	Processing of fruits and vegetables (also oily and fatty) at very low temperatures
<b>Food industry</b>	Transport of unpacked food in freezers
<b>General material handling</b>	Horizontal conveying also at very low temperatures

### Order information

<b>Article number</b>	908922
<b>Suitable for corrugated side walls</b>	Yes
<b>Belt style</b>	PF = PolarFlex
<b>Standard delivery width</b>	1829 mm / 72.01 in
<b>Longitudinal seam possible</b>	Yes

### PF200 LT AR OFR CxF-NA blue FDA

#### Construction

<b>Top face material</b>	Polyvinyl chloride, low temperature & abrasion resistant
<b>Surface pattern</b>	Smooth
<b>Coating thickness</b>	1.02 mm / 0.04 in
<b>Color</b>	Blue
<b>Driving face material</b>	Polyvinyl chloride, low temperature & abrasion resistant
<b>Surface pattern</b>	Fabric
<b>Coating thickness</b>	0.1 mm / 0.004 in
<b>Color</b>	Blue
<b>Tension member material</b>	3-ply interwoven fabric of polyester spun warp and weft
<b>Number of fabric plies</b>	1

#### Technical data

<b>Total thickness</b>	5.08 mm ± 0.38 0.2 in ± 0.015
<b>Weight</b>	6.35 kg/m <sup>2</sup> ± 0.48 1.3 lbs/ft <sup>2</sup> ± 0.097
<b>k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005</b>	13.13 N/mm / 75 lbf/in
<b>Recommended Elongation at fitting min.</b>	0.5 %
<b>Recommended Elongation at fitting max.</b>	1.5 %
<b>Rated working tension</b>	35 N/mm / 200 lbf/in at 2 % Elongation
<b>Friction coefficient of driving face against steel panel according ISO 21182</b>	0.45
<b>Friction coefficient of top face against steel panel according ISO 21182</b>	0.85
<b>Permissible operating temperature</b>	-40/82 °C -40/180 °F
<b>Hardness of top face coating as per DIN 53505 (Shore A)</b>	70

### PF200 LT AR OFR CxF-NA blue FDA

#### Properties

<b>Lateral stiffness</b>	Laterally flexible
<b>Troughable</b>	Yes
<b>Suitable for accumulation</b>	No
<b>Inclined conveying</b>	No
<b>Suitable for knife edges</b>	No
<b>Suitable for curves</b>	No
<b>Flame-retardant</b>	No
<b>Noise development</b>	Normal
<b>Particular surface properties</b>	<ul style="list-style-type: none"> <li>▸ Good grip</li> <li>▸ Coating/fabric abrasion especially resistant</li> </ul>
<b>Coating/fabric exceptionally cut resistant</b>	Yes
<b>Belt support</b>	Support rollers
<b>UV resistance</b>	Normal

#### Food properties

<b>FDA 21CFR</b>	Suitable for the transport of unpacked Food in compliance with FDA regulation 21CFR
------------------	---

#### Electrostatic properties

<b>Not antistatic</b>	Belt material with electrically insulating properties
-----------------------	---

#### Fabrication

<b>Suitable for corrugated side walls</b>	Yes
<b>Profiles on top face</b>	Yes
<b>Profiles on underside</b>	Yes
<b>Mechanical fasteners</b>	Alligator®RS187; Clipper® #4; Clipper® U4

### PF200 LT AR OFR CxF-NA blue FDA

#### Minimum drum diameter

<b>Z-splice, counter-bending</b>	89 mm / 3.5 in
----------------------------------	----------------

<b>Mechanical Alligator® fastener, bending</b>	102 mm / 4 in
--	---------------

<b>Mechanical Clipper® fastener, bending</b>	102 mm / 4 in
--	---------------

#### Remarks

► **Polarflex™: very low temperature belting with improved abrasion resistance.**

<b>Chemical resistance</b>	V
----------------------------	---

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 5/16/2025 1:02:33 PM