

### Product Data Sheet

# PVC150 OFR CTxF-NA royal blue FDA

#### Applications

<b>Agriculture</b>	Processing of fruits and vegetables (also oily and fatty)
<b>Fish industry &amp; meat industry</b>	Meat processing; Seafood processing
<b>Food industry</b>	Processing of food (also oily and fatty)
<b>General material handling</b>	Horizontal conveying; Troughed conveyor belt

#### Order information

<b>Article number</b>	908943 Copy1
<b>Suitable for corrugated side walls</b>	Yes
<b>Belt style</b>	PVC = Interwoven PVC
<b>Standard delivery width</b>	1829 mm / 72.01 in
<b>Longitudinal seam possible</b>	On request

#### Construction

<b>Top face material</b>	Polyvinyl chloride, oil and fat resistant
<b>Surface pattern</b>	Smooth
<b>Coating thickness</b>	1.02 mm / 0.04 in
<b>Color</b>	Signal blue (~RAL 5005)
<b>Driving face material</b>	Polyvinyl chloride, oil and fat resistant
<b>Surface pattern</b>	Fabric
<b>Coating thickness</b>	0.1 mm / 0.004 in
<b>Color</b>	Signal blue (~RAL 5005)
<b>Tension member material</b>	2-ply interwoven fabric of polyester spun warp and weft
<b>Number of fabric plies</b>	1

### PVC150 OFR CTxF-NA royal blue FDA

#### Technical data

<b>Total thickness</b>	6.52 mm 0.257 in
<b>Weight</b>	
<b>k1% value relaxed (effective pull at 1% elongation), established in line with ISO 21181:2005</b>	9.63 N/mm / 55 lbf/in
<b>Recommended Elongation at fitting min.</b>	0.5 %
<b>Recommended Elongation at fitting max.</b>	1.5 %
<b>Rated working tension</b>	26 N/mm / 150 lbf/in at 2 % Elongation
<b>Friction coefficient of driving face against steel panel according ISO 21182</b>	0.45
<b>Permissible operating temperature</b>	-18/82 °C 0/180 °F
<b>Hardness of top face coating as per DIN 53505 (Shore A)</b>	65

#### Properties

<b>Lateral stiffness</b>	Laterally flexible
<b>Troughable</b>	Yes
<b>Suitable for accumulation</b>	No
<b>Inclined conveying</b>	No
<b>Suitable for knife edges</b>	No
<b>Suitable for curves</b>	No
<b>Flame-retardant</b>	No
<b>Noise development</b>	Normal
<b>Particular surface properties</b>	► Good grip
<b>Belt support</b>	Support rollers
<b>UV resistance</b>	Normal

#### Food properties

<b>FDA 21CFR</b>	Suitable for the transport of unpacked Food in compliance with FDA regulation 21CFR
------------------	-------------------------------------------------------------------------------------

### PVC150 OFR CTxF-NA royal blue FDA

#### Electrostatic properties

<b>Not antistatic</b>	Belt material with electrically insulating properties
-----------------------	-------------------------------------------------------

#### Fabrication

<b>Suitable for corrugated side walls</b>	Yes
<b>Profiles on top face</b>	Yes
<b>Profiles on underside</b>	Yes
<b>Mechanical fasteners</b>	Alligator®RS125; Clipper® G006; Clipper® U2

#### Minimum drum diameter

<b>Z-splice, counter-bending</b>	89 mm / 3.5 in
----------------------------------	----------------

#### Remarks

<b>Chemical resistance</b>	V
----------------------------	---

The physical data in this data sheet is approximate, can alter depending on production environments and was established at standard ambient conditions (23°C/73°F, 50% relative humidity) in accordance with DIN 50014/ISO 554. Fluctuations in climate can cause variations.

Date of last change: 6/20/2025 1:40:29 PM